ISLC-25 ½ Century Anniversary Wrkshp 2016 Diode Laser Active Region Evolution Peter Zory – University of Florida

1962 to 1970

Diode Lasers: Diffused & Epitaxial GaAs P-N Junctions Heterojunction Structures: Single SH & Double DH

1970 to 1980

Two Dimensional Waveguides 2D

Corrugated Waveguides

Distributed Feedback DFB / Grating Coupling GC

1980 to 1990


Compact Disc CD / Digital Video Disc DVD

8th Transatlantic Communications Cable TAT-8

Quantum Well QW / Photonic Integrated Circuit PIC

Vertical Cavity Surface Emitting Laser VCSEL

1st Diode Laser – Diffused P-N Junction 1962




US Patent 3,245,002 filed 24 October 1962 R. N. Hall General Electric

? Useful Power @ Room Temp 300°K

Replace Diffused P-N Junctions Liquid Phase Epitaxy LPE


Graphite Cylinder





Epitaxial Laser Material

Active Region Thickness d ≈ 2μm



"Average" threshold current density

J_{th} ≅ 30,000 Amps/cm² @ 300⁰K

Commercial Products pulsed diode lasers & high power laser arrays

GALLIUM-ARSENIDE INJECTION-LASER DIODE FOR PULSE OPERATION



RCA Dev. Type TA2628 is a p-n junction gallium arsenide injection-laser diode which emits radiation, when forward biased, in the near infrared region of the spectrum. It is supplied in a modified TO-46 package with a low-absorbing glass window. It has alloyed contacts in both regions of its junction to provide good reliability and high thermal conductivity.

The TA2628 is designed especially for pulse operation with high modulation rates at room tempera ture. However, it may be operated in such service within the temperature range of -196° C to +50° C. It will have high power output and high power efficiency. The TA2628 is well suited for communications, ranging and guidance systems, instrumentation, control equipment, and other applications utilizing nanosecond pulse widths at high repetition rates.

Radiation from the TA2628 is emitted in a direction perpendicular to the plane of the header. Beam spread at room temperature is 150 in a plane parallel to and 50 in a plane perpendicular to the junction. Although beam spread increases slightly with increasing operating temperature, it may be reduced to a fraction of a degree at all temperatures by means of a suitable optical lens.



- Wavelength of Peak Emission at 27° C - 9050 + 50 &
- High Peak Power Output -2 Watts Typical at Peak Pulse Current of 30 Amperes
- High Power Efficiency -Typically 0.5% at 27° C and Peak Pulse Current of 30 Amperes

DATA

Wavelength of Peak Emission at +27° C (300° K):

For further information or application assistance on this device, contact your RCA Field Representative or write RCA Solid State Optical Product Marketing, RCA, Somerville, N. J.

INFORMATION FURNISHED BY RCA IS BELIEVED TO BE ACCURATE AND RELIABLE, HOWEVER, NO RESPONSIBILITY IS ASSUMED BY RCA FOR ITS USE; NOR FOR ANY INFRINGEMENTS OF PATENTS OR OTHER RIGHTS OF THIRD PARTIES WHICH MAY RESULT FROM ITS USE, NO LICENSE IS GRANTED BY IMPLICATION OR OTHERWISE UNDER ANY PATENT OR PATENT RIGHTS OF RCA



RADIO CORPORATION OF AMERICA ELECTRONIC COMPONENTS AND DEVICES

HARRISON, N.J.

T 506-1 3-66 Trademark(s) ® Registered Marca(s) Registrada(s) Printed in U.S.A.

1966

RCA GaAs Pulsed Laser

300°K 2 W out @ 30 A


pulse width < 200 ns

wavelength 905 nm



TYPE LA 0800-01 DEVELOPMENTAL

800 WATT GALLIUM ARSENIDE LASER ARRAY



SPERRY
ELECTRO-OPTICS GROUP
SPERRY GYROSCOPE DIVISION
GREAT NECK, N.Y. 11020
PHONE 516 - 574 - 2292

Sperry Rand GaAs Laser Array

300°K 800 W out @ 150 A

80 ns pulse width

Wavelength 915nm

Sands Hotel





Celebrities



Howard Hughes



Sammy Davis Jr.

- * Epitaxial GaAs P-N Junction lasers turn-on delay and modulation speeds
- * Stripe geometry lasers beam instabilities with current change
- Homojunction laser theory peak optical gain g vs current density J
- * ? Is Continuous Wave CW operation possible @ 300°K?

Paper V-1 IBM Research


"Stimulated emission from $Ga_{1-x}Al_x$ As diodes" $\lambda = 750 \text{ nm at } 77^0\text{K}$

J. Quantum Electronics v4 p68 January 1968

Single Heterojunction **SH** Structure

1968

Material grown by Single Layer LPE




Typical threshold current density

$$J_{th} \approx 8,000 \text{ Amps/cm}^2 @ 300^0 \text{K}$$

? Double Heterojunction DH Possible ? 1968

? How Does One Make a Multilayer Structure ?




Carriers confined in photon amplifying layer - thickness d

Photons confined in 1D waveguide mode - width w_m

Active Region: d enclosed in w_m

Substrate Slider Design for Multilayer LPE Growth




US patent application filed on above design in February 1969 RC

ISLC-2 Mexico City Discussion topics

* Single Heterojunction SH lasers: turn-on delay and reliability issues

* Close Confined Lasers - (DH acronym not yet used)

Active Region: gain layer of width d enclosed in 1D mode width w_m problem: "rabbit-ear" modes perpendicular to junction plane



DH structure used in first 300°K CW diode laser Early Summer 1970

Ioffe Institute, Russia Bell Laboratories, USA


- *Lifetime DH lasers operating CW at 300°K self pulsing (≈ 500 Mb/sec) bad for com laser 1D waveguide with 3 layers
 - 1D waveguide with 4 layers

 Large optical cavity LOC structure
 - 1D waveguide with 5 layers

 Local Gain Region LGR structure


 or Separate Confinement Heterostructure SCH
 - 2D waveguide: Carriers & Photons Confined in 2D Mesa-Stripe-Geometry DH Laser

ISLC-3 Mesa-Stripe-Geometry DH Laser 1972




ISLC-3 Boston paper PD2 Hitachi Ltd "Optical Characteristics of Mesa-Stripe-Geometry DH Lasers" Applied Physics Letters v20 p344 May 1972

ISLC-8 1st mass-produced laser-CD players 1982 CD wavelength standard λ = 780 nm



ISLC-10 Red DH laser operating CW 300K 1986



ISCL-10 Kanazawa paper A-1 Toshiba Corp. "Low Threshold Current InGaP/InAIP Transverse Mode Stabilized Laser" Applied Physics Letters v 48 p207 1986

- * DH laser reliability: dark-line-defect DLD / transient effects
- * DH & SCH laser performance: optimal active layer thickness d
- * Cryogenic Lead-Salt lasers operating in the mid-infrared
- * New 2D waveguide structure buried heterojunction BH
- * New 1D active region


corrugated waveguide narrow spectral band operation single longitudinal mode **SLM** Distributed Feedback DFB Laser

ISLC-4 DH laser - corrugated active region 1974

Distributed Feedback DFB Laser pulsed operation 80°K Cr-Au Au-Ge-Ni corrugation period **Λ** ≅ 347 nm output p-GaAs active layer d = 1000 nm

ISLC-4 Atlanta paper B5 Hitachi Ltd / Cal Tech"GaAs-GaAlAs DH Injection Lasers with DFB"Jrnl Quantum Electronics v11 p436 July 1975


ISLC-9 Buried Heterostructure BH-DFB 1984



ISLC- 9 Rio paper A-1 Hitachi Ltd "Optimization of Device Parameters for Low I_{th} DFB Lasers"

TAT-8 1988


1st TransAtlantic Cable providing telephone service via pulsed laser light



- * DH laser reliability: dark-line-defect DLD / transient effects
- * DH & SCH laser performance: optimal active layer thickness
- * Cryogenic Lead-Salt lasers operating in the mid-infrared
- * New 2D waveguide structure buried heterojunction BH
- * New 1D active region corrugated waveguide wide aperture surface emission **Grating Coupled Surface Emitting Laser GCSEL**

ISLC-4 DH laser - corrugated active region 1974

Grating Coupled Surface Emitting Laser GCSEL 300°K pulsed




ISLC-4 Atlanta paper PD-2 IBM Research"Grating Coupled GC AlGaAs DH Diode Lasers"Jrnl Quantum Electronics v11 p451 July 1975



GC Substrate Emitting DFB Laser GCSEL


2010



IEEE Photonics Society Summer Topicals paper MA1.1 9 July 2012 SPIE Proceedings v7686 p76860J-1 2010 Alfalight

1st quantum well QW laser

1975



Applied Physics Letters v26 p465 April 1975 AT&T Bell Labs

ISLC-5

Nemu-No-Sato

1976



ISLC-5 Nemu-No-Sato Discussion topics 1976

* Elimination of "Kinks" in Output Power vs Current Profiles

AlGaAs/GaAs Structures for stabilizing 2D waveguide modes "Simple" very narrow stripe 2D waveguides:
 gain/loss, implanted ions, dielectric layers
 Complex structure 2D waveguides:
 transverse junction stripe TJS, embedded, loaded

* Corrugated waveguide structures:

single frequency **DFB** lasers / surface emission **GCSELs**

Long distance fiber communication potential

Paper L-V-7 Lincoln Lab USA "(InGa) (AsP) / InP DH structure Lasers" $\lambda = 1.1 \mu m @ 300^{\circ} K$

Applied Physics Letters v28 p283 1976


- * Long Wavelength InGaAsP lasers: ~ 30% of total papers 9 general type papers 9 papers directly related to temperature sensitivity
- * Reliability issues:

 now mostly InGaAsP/InP lasers AlGaAs/GaAs proven
- * Mode hopping noise in single longitudinal mode **SLM** lasers stabilized **2D** waveguide mode AlGaAs lasers
- * New type of active region

 "Surface Emitting Injection Laser"

 later to be known as the VCSEL

ISLC-8 Vertical Cavity Surface Emitting Laser 1982 VCSEL



ISLC-8 Ottawa paper 37 Tokyo Inst Technology "SLM Oscillation of 10 μm cavity-length Surface Emitting Injection Lsr" Japanese J Appl Phys v18 p2329 1979

ISLC-9 Rio de Janeiro Discussion Topics 1984

* Most controversial issue

What's the best **SLM** structure for long distance optical fiber communication systems? the **CHIRP** problem present modulation bandwidth ~ 10GHz


- * Most Popular topics: 15 papers each high power and single longitudinal SLM mode lasers
- * Quantum Well QW lasers: 9 papers

 Temperature dependence of threshold T₀

*High Power

Non-absorbing mirror NAM laser
1.5 Watt - 100ns pulse - high quality beam

ISLC-9 Hgh Pwr Non-Absorbing Mirror NAM Lsr 1984 Constricted DH Large Optical Cavity LOC Active Region



"Non-absorbing-Mirror NAM CDH-LOC Lasers" IEEE Spectrum v22 p43 June 1985

ISLC-11 Boston Discussion Topics

* Most Popular Topic

27% of papers had DFB/DBR acronym in title; popularity due to both long distance telecom & coherent communications needs

* High Power:

first 100mW VCSEL - order of magnitude improvement first strained QW laser paper at an ISLC conference

* Quantum Well QW lasers


* High Speed Modulation / Tunable lasers

high-speed, direct detection, coherent heterodyne detection systems wavelength-division-multiplexing WDM photonic Integrated circuit PIC

ISLC-11

Tunable MQW DBR PIC


1988



ISLC-5 Boston paper J1 AT&T Bell Labs

"High Performance Tunable 1.5 μm InGaAs/InGaAsP MQW DBR Lasers"

Applied Physics Letters v53 p1036 1988




- * The Big Question Not Answered at ISLC-12 Why aren't QW lasers as fast as predicted?
- * High Power: **E2** facet treatment process "eliminates" catastrophic optical damage **COD**
- * Strained QW Lasers

sub-mA threshold in λ = 1.5 μ m region InGaAsP/InP laser performance enhanced using **tensile or compressive** strained **QW** tunable **VCSEL** narrow line-width, single InGaAs **QW VCSEL**

sub-mA CW threshold at 300°K


ISLC-12 CW 300°K VCSEL single QW active layer 1990




ISLC-12 Davos paper B-1 UC Santa Barbara"Narrow Linewidth, Low Threshold VCSELs"Applied Physics Lttrs v57 p1605 1990

1st Diode Laser

1962



US Patent 3,245,002 filed 24 October 1962 R. N. Hall General Electric



UK

P Zory

ISLC International Semiconductor Laser Conference

1967 to 1990			commercially available	
#	Year	Active Layer	CW Power	Digital Speed
		thk ' <mark>d</mark> ' nm	quality beam	Mb/s
1	1967	≈ 2000	reliable mW	
2	' 69	≈ 1000		
3	'72	200		0.01
4	'74			
5	'76	100	5	
6	'78			45
7	'80		15	275
8	'82			
9	'84		20	400
10	'86	10		
11	'88		40	
12	'90	5	100	1000
				P Zory